

THERMglass™ Premium VI

A Premium Performance Type VI Fiberglass Ply Sheet

FEATURES

Higher quality glass plies

Multi-ply system

Maintainable areas

Surfacing options

UL, FM, and Florida Building
Code Listed

BENEFITS

- Stronger than standard Type IV glass felts
- Consistent component to accept hot-melt adhesive and produce high quality roof
- Non-rotting

- Redundant waterproofing
- Time-tested reliable installation techniques of conventional built-up roofing

- Long service life. Modification to roof-top readily accommodated

- Can be finished with various methods to meet local requirements

- Fire/wind protection

DESCRIPTION

THERMglass Premium VI is a heavy duty, fiberglass ply sheet that exceeds ASTM D 2178, Type VI and CSA A123.17, Type VI specifications.

BASIC USES

THERMglass Premium VI is designed as a high performance ply sheet within modified bitumen or built-up roofing systems for application over preformed rigid insulation and base sheets. It may be used with Premium III or Premium IV Asphalt. Where an extra level of performance is required, THERMastic 80 or THERMastic Hot-Melt Adhesive is recommended.

PACKAGING

Available in rolls are 36" (914.4 mm) wide, 500 ft²/roll (46.4 m²/roll) applied. Sold by pallet, with 25 rolls per pallet

APPLICATION

General Application Data: Roof replacement usually involves more complexities than new construction roofing. Often encountered are situations such as rusted/deteriorated decks, rotted wood components, rooftop equipment which cannot be moved or shut down, and numerous other conditions.

The following application information is designed to serve as a general guide. Your local Tremco Representative will prepare detailed specifications based upon your roof's conditions.

Structural Deck: Must be properly designed and structurally sound.

Drainage: Ponding conditions are unacceptable and will adversely affect performance of any roofing system. If positive drainage does not exist, water removal must be facilitated by lowering drains, and/or installing additional drains, tapered insulation, or a Tremco approved lightweight insulating concrete slope system.

Insulation: Insulation must be dry and kept dry. No more insulation shall be installed than can be covered that day.

Installation Procedures: According to particular job specifications, prepare surface to be covered:

- Replace areas of wet insulation, deteriorated deck, and wood components.
- Install roof insulation or base sheet.

Plan placement of THERMglass Premium VI Roofing Ply to ensure that water will flow over or along, but not against exposed edges.

Starting at low point of roof, apply uniform and continuous mopping of the specified hot-melt adhesive using a standard roofing mop or Tremco approved felt layer.

Two ply base under POWERply MB: Start and finish roof membrane along edges, terminations, and projections. Use starting/finishing strips; 18" and 36" (457 and 914 mm) wide plies.

THERMglass Premium VI

APPLICATION CONTINUED

Install THERMglass Premium VI in shingle fashion. Overlap starter strips 20" (508 mm) with the first ply then overlap each succeeding ply 19" (482 mm).

Three ply membrane: Start and finish roof membrane along edges, terminations and projections, use starting/finishing strips; 12, 24, and 36" (305, 610, 914 mm) wide plies.

Install THERMglass Premium VI in shingle fashion. Overlap starter strips 26" (660 mm) with first ply, then overlap each succeeding ply 24-2/3" (626 mm).

Four ply membrane: Start and finish roof membrane along edges, terminations and projections, use starting/finishing strips: 9, 18, 27, and 36" (229, 457, 685, 914 mm) wide plies.

Install THERMglass Premium VI in shingle fashion. Overlap starter strips 29" (737 mm) with first ply, then overlap each succeeding ply 27-1/2" (699 mm).

Interply adhesive: Embed each ply in uniform and continuous mop-ping of specified hot-melt adhesive. Ply shall never touch ply. Apply specified hot-melt adhesive no more than 10' (3 m) ahead of each roll. Lightly broom plies from unmopped side to ensure complete adhesion. Overlap previous work 24" (600 mm). Lap ply sheet ends 6" (150 mm). Extend all plies to top edges of all cants and cut excess evenly. Stagger end laps.

Avoid walking on plies until adhesive has cooled.

MB/BUR Interply: 25 lb/100 ft² (1.2 kg/m²) ± 20% Install flashing as specified.

Gravel and smooth surfacing options are available. Consult your local Tremco Representative for specific surfacing options.

- Not intended to perform under ponding conditions. Positive drainage is required.
- Do not apply when ambient temperature prevents installation of hot-melt adhesives within stated application temperature range.
- Do not expose to solvents, oils, or other contaminants harmful to asphaltic materials.

APPLICATION RATE

SURFACING OPTIONS

LIMITATIONS

PHYSICAL PROPERTIES

PROPERTY	TYPICAL VALUE	TEST METHOD
Breaking strength	60 lbf/in (10.6 kN/m) MD & XMD minimum	ASTM D 146
Net dry mass of asphalt impregnated glass felt, individuals rolls	6.9 lbs/SQ (334 g/sqm)	ASTM D 146
Mass of desaturated glass felt	1.9 lbs/SQ (92 g/sqm)	ASTM D 146
Bituminous saturant (asphalt)	5.0 lbs/SQ (245 g/sqm)	ASTM D 146
Pliability, 1/2 in. (13 mm) radius bend	No failures	ASTM D 146

MAINTENANCE

Your local Tremco Roofing Sales Representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventative maintenance are all part of a sound roof program.

PRECAUTIONS

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

TECHNICAL SUPPORT

Your local Tremco Roofing Sales Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.



www.tremcoroofing.com
3735 Green Road
Beachwood, Ohio 44122
1.800.852.6013

220 Wicksteed Avenue
Toronto, Ontario, M4H 1G7
1.800.668.9879

Tremco Roofing and Building Maintenance is part of Tremco Construction Products Group.

Tremco is a US Registered trademark of Tremco CPG Inc.

The information provided on this data page supersedes all previous data concerning this product and its application.

The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.